

Topological Order in the Phase Diagram for High-Temperature Superconductors with Point Defects

Jan Kierfeld

Institut für Theoretische Physik der Universität zu Köln, D-50937 Köln, Germany

Materials Science Division, Argonne National Laboratory, Argonne, IL 60439

(December 10, 1997)

Abstract

Applying a Lindemann-like criterion obtained previously by Kierfeld, Nattermann and Hwa [Phys. Rev. B **55**, 626 (1997)], we estimate the magnetic field and temperature for a high- T_c superconductor, at which a topologically ordered vortex glass phase becomes unstable with respect to a disorder-induced formation of dislocations. The employed criterion is shown to be equivalent to a conventional phenomenological Lindemann criterion including the values for the numerical factors, i.e., for the Lindemann-number. The positional correlation length of the topologically ordered vortex glass is calculated.

I. INTRODUCTION

The influence of disorder on the Abrikosov vortex lattice in the mixed phase of high-temperature superconductors, such as $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ (YBCO), is an issue of immediate technological interest because pinning of the flux lines by disorder opens the possibility of regaining a dissipation-free current flow in the mixed phase. The flux line (FL) array in a high-temperature superconductor (HTSC) is extremely susceptible to thermal and disorder-induced fluctuations due to the interplay of several parameters, namely the high transition temperature T_c , large magnetic penetration depths λ and short coherence lengths ξ , and

a strong anisotropy of the material. This leads to the existence of a variety of fluctuation dominated phases of the FL array and very rich phase diagrams for the HTSC materials [1]. We want to consider here the pinning of FLs by point defects such as the oxygen vacancies, which is usually referred to as point disorder. It is well-known that the FL lattice is unstable to point disorder [2]. It has been conjectured that due to a *collective pinning* by the point disorder, the FL array may form a *vortex glass phase* with zero linear resistivity [3–6]. Although the existence of a vortex glass (VG) phase has been verified experimentally [7–11], its large scale properties characterizing the nature of the VG phase are still under debate [1]. A possible scenario for a description of the low-temperature properties of the FL array subject to point disorder is the existence of a topologically ordered, i.e., *dislocation-free* VG phase, the so-called *Bragg glass* phase [12] as a thermodynamically stable phase. In this glassy phase, a quasi long range positional order of the FL array is maintained in spite of the pinning [5,12]. This entails the existence of algebraically decaying Bragg peaks in diffraction experiments on this phase (bearing the name “Bragg glass” for this property), which have indeed been observed in neutron diffraction experiments on $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ (BSCCO) at low magnetic fields [13]. In the Bragg glass phase, the disordered FL array is modeled as an elastic manifold in a periodic random potential, similar to a randomly pinned charge density wave or a XY model in a random field [14–16,12]. To give a thermodynamically stable phase, this requires the persistence of the topological order, or absence of unbound dislocations, even in the presence of disorder. In the neutron diffraction experiments by Cubitt et al. [13], it has been observed that upon increasing the magnetic field, the Bragg peaks vanish, indicating an instability of the Bragg glass phase. Critical current measurements of Khaykovich et al. [17] show a sharp drop in the (local) critical current j_c upon decreasing the magnetic induction below a critical value. This can be attributed to the “disentanglement” of FLs in the absence of dislocations when topological order is regained and dislocation loops vanish upon lowering the magnetic field. Similarly, changes in the I-V characteristics of YBCO based superlattices below a critical magnetic field can be interpreted as stemming from a sharp drop of the pinning energy and indicate a restoration of positional order in the

VG [18]. The existence of a topological transition has also been demonstrated in recent numerical studies [19,20]. In the closely related 3D XY model in a random field, vortex loops occur in a topological phase transition at a critical strength of the random field [19]. In simulations of disordered FL arrays [20], a proliferation of dislocation lines has been found at a critical magnetic field in good agreement with the experimental results in Ref. [13].

Recently, the quantitative aspects of this issue have been addressed also analytically [21–25]. In Ref. [21] a self-consistent variational calculation and a scaling argument are presented, which show the topological stability of the elastic Bragg glass phase over a finite range of parameters that can be estimated by a Lindemann-like criterion (1). A more detailed discussion of the methods used in Ref. [21] and their limitations as well as of the Lindemann-like criterion (1), which provides the basis for the calculations in the present work, will be given in the next paragraph. Recently, Fisher [22] has presented refined scaling arguments further supporting the existence of a topologically ordered Bragg glass phase. In Refs. [23–25], purely phenomenological Lindemann criteria are used as starting point for an estimate of the phase boundaries of the Bragg glass. Ertaş and Nelson [23] and Goldschmidt [24] use “cage models” to mimic the interactions between FLs which yields an effective theory for a single FL in a random potential, to which they apply the conventional phenomenological Lindemann criterion. Giamarchi and Le Doussal [25] apply a slightly modified phenomenological Lindemann criterion of the form $\overline{\langle u^2 \rangle}(l) < c_L^2 l^2$, where $\overline{\langle u^2 \rangle}(l)$ is the (disorder-averaged) *relative* mean square displacement of neighbouring FLs separated by the FL spacing l (c_L is the Lindemann-number). However, it is well known that phenomenological Lindemann criteria as used in Refs. [23–25] do not allow a theoretical description of a phase transition but can only give estimates of the location of the transition. They rely on the assumption that the phase transition reflects in the short scale behaviour of the system. Also the variational calculation and the scaling argument presented in Ref. [21] cannot give a complete description of the transition as only a detailed renormalization group (RG) analysis of the problem would allow which is not yet available. The refined scaling arguments of Ref. [22] represent a further step towards this goal.

In Ref. [21], the stability of the elastic Bragg glass phase has been investigated for a layered uniaxial geometry, where the magnetic field is parallel to the CuO-planes, by means of a self-consistent variational calculation and a scaling argument identifying the shear instability due to proliferating dislocations by the disorder-induced decoupling of the layers. For this geometry a Lindemann-like criterion has been derived, which is given below in (1) and relates the stability of the Bragg glass phase to the ratio of the positional correlation length and the FL spacing. These findings are supported by a more rigorous RG analysis [26,27] for a simplified model with only two layers of FLs in a parallel magnetic field. The usual experimental situation with the magnetic field perpendicular to the CuO-layers, which will be considered in the present work, is theoretically less understood mainly because displacements of the FLs have two components (biaxial) instead of one component (uniaxial). It is unclear at present whether topological phase transitions of the biaxial and uniaxial model share the same universality class [22]. In Ref. [21], it has been argued that the scaling argument for the uniaxial geometry can be generalized to the full, biaxial model leading to the following criterion estimating the range of stability of the Bragg glass phase with respect to a spontaneous formation of dislocation loops:

$$R_l > c^{1/2\zeta} (l^2 + \lambda^2)^{1/2} \simeq c^{1/2\zeta} \max \{l, \lambda\} . \quad (1)$$

l is the FL distance and λ the magnetic penetration depth (we consider a magnetic field perpendicular to the CuO-planes of the HTSC, and will specify λ below for such a geometry). R_l is the (transversal) *positional correlation length* of the disordered FL array, which is defined as the crossover length to the asymptotic large scale behaviour of the Bragg glass phase, where the average FL displacement starts to exceed the FL spacing l , see (23). c is a number, which was obtained in Ref. [21] to be of the order of $c \approx \mathcal{O}(50)$, and $\zeta \approx 1/5$ is the roughness exponent of the pre-asymptotic so-called “random manifold” regime, see (24) below. At the boundaries of the regime given by (1), a topological transition occurs, and dislocations proliferate. Beyond the transition line the FL array may form an amorphous VG with vanishing shear modulus or a viscous FL liquid.

This article is divided into three parts. First, we will review the pre-asymptotic regimes of the FL array subject to point disorder on scales smaller than the positional correlation length R_l . This allows us to express R_l in terms of the microscopic parameters of the HTSC and the disorder strength, and to obtain its dependence on magnetic induction B and temperature T . In the second part, we will demonstrate the equivalence of the above criterion (1) to the phenomenological Lindemann criterion in the form $\overline{\langle u^2 \rangle}(l) < c_L^2 l^2$ (as for example used in Refs. [25]), where $\overline{\langle u^2 \rangle}(l)$ is the (disorder-averaged) *relative* mean square displacement of neighboured FLs. This yields a relation $c \approx c_L^{-2}$ between c from (1) and the Lindemann-number c_L , and the value $c \approx \mathcal{O}(50)$ found by a variational calculation in Ref. [21] turns out to be in good agreement with a value $c_L \approx 0.15$ widely used in the literature for the Lindemann-number. This equivalence further supports a scenario where the topological transition of the FL array subject to point disorder may be described as disorder-induced melting by unbound dislocations on the shortest scale l [21]. Finally, and most importantly from the experimental point of view, we estimate the region of the phase diagram of YBCO in the B-T plane (see Fig. 1) where the Bragg glass phase is stable and should be observable experimentally or numerically according to the Lindemann-like criterion (1). We find qualitative agreement with experiments [18]. The upper phase boundary of the Bragg glass, which we obtain using (1), turns out to be identical to the one obtained by Ertaş and Nelson [23].

II. POSITIONAL CORRELATION LENGTH

To relate the positional correlation length R_l to the microscopic parameters of the HTSC and the disorder strength, we have to review the crossover between the different pre-asymptotic regimes of the dislocation-free disordered FL array preceding the asymptotic Bragg glass phase, and the associated crossover length scales [1]. These crossovers are induced by the interplay between the FL interaction, the periodicity of the FL lattice and the disorder potential, which are in addition affected by thermal fluctuations, and lead

to essentially two different pre-asymptotic regimes: On the shortest scales, we have the “Larkin” or “random force” regime of Larkin and Ovchinnikov [2], which crosses over to the so-called “random manifold” regime at the Larkin length, before the asymptotic Bragg glass behaviour sets in on the largest scales exceeding the positional correlation length. In between this sequence of crossovers, one additional length scale is set by the FL interaction, which describes a crossover from a “single vortex” behaviour to a “collective” behaviour.

In the following, we consider the usual experimental situation $\mathbf{H} \parallel \mathbf{c}$ of a magnetic field perpendicular to the CuO-planes of the HTSC. FL positions are parameterized by the two-component displacement-field $\mathbf{u}(\mathbf{R}, z) = \mathbf{u}(\mathbf{r})$ in a continuum approximation of the Abrikosov lattice, where $\mathbf{R}$ is the vectors in the $\mathbf{ab}$ -plane and z is the coordinate in the $\mathbf{c}$ -direction, or by the Fourier transform $\tilde{\mathbf{u}}(\mathbf{K}, k_z) = \tilde{\mathbf{u}}(\mathbf{k})$. Let us adopt the convention to denote scales longitudinal to the FLs in the z -direction by L and transversal scales in the $\mathbf{ab}$ -plane by R . Moreover, it turns out to be convenient to use the *reduced induction* $b \equiv B/B_{c2}(T) = 2\pi\xi_{ab}^2/l^2$ to measure the strength of the magnetic field.

A. Interaction-induced Length Scale L^*

The dislocation- and disorder-free FL array can be described by elasticity theory (see Ref. [1] for a review) in the displacement field $\mathbf{u}$ with the elastic moduli c_{11} , c_{44} and c_{66} , which can in general be dispersive (i.e., $\mathbf{k}$ -dependent in Fourier-space) due to the non-locality of the FL interaction. Except for extremely low magnetic fields, the FL lattice is essentially incompressible ($c_{11} \gg c_{66}$), and we can neglect longitudinal compression modes to a good approximation. Note also, that the shear modulus c_{66} is non-dispersive, because volume-preserving shear modes are not affected by the non-locality in the FL interaction. Then, the elastic Hamiltonian in the remaining transversal part $\tilde{\mathbf{u}}_T$ of the displacement field is of the form:

$$\mathcal{H}_{el}[\tilde{\mathbf{u}}_T] = \frac{1}{2} \int \frac{d^2\mathbf{K}}{(2\pi)^2} \frac{dk_z}{2\pi} \left\{ c_{66}(\mathbf{K} \times \tilde{\mathbf{u}}_T)^2 + c_{44}[K, k_z](k_z \tilde{\mathbf{u}}_T)^2 \right\} \quad (2)$$

The dispersion-free shear modulus is given by $c_{66} \approx \epsilon_0/4l^2$ in the dense limit $l/\lambda_{ab} = (b/2\pi)^{-1/2}/\kappa < 1$ (with $\kappa = \lambda_{ab}/\xi_{ab}$), and exponentially decaying $c_{66} \propto \exp(-l/\lambda_{ab})\epsilon_0/l^2$ in the dilute limit $l/\lambda_{ab} > 1$. $\epsilon_0 = (\Phi_0/4\pi\lambda_{ab})^2$ is the basic energy (per length) scale of the FL. As estimates for YBCO we use $\xi_{ab}(0) \approx 15\text{\AA}$, $\epsilon_0(0)\xi_{ab}(0) \approx 1300\text{K}$ and $\kappa \approx 100$ [1].

The tilt modulus $c_{44} = c_{44}[K, k_z] = c_{44}^b[K] + c_{44}^s[k_z]$ is dispersive with the bulk-contribution

$$c_{44}^b[K] \simeq \frac{\epsilon_0}{l^2} \frac{K_{BZ}^2 \lambda_{ab}^2}{1 + K^2 \lambda_c^2 + k_z^2 \lambda_{ab}^2} \quad (3)$$

dominating in the dense limit well within the Brillouin zone (BZ) $K < K_{BZ} = 2\sqrt{\pi}/l$ (approximated by a circular BZ) and the *single vortex tilt modulus* $c_{44}^s = c_{44}^s[k_z]$ [28]

$$\begin{aligned} c_{44}^s[k_z] &= c_{44}^{s,J} + c_{44}^{s,em}[k_z] \\ &\simeq \frac{\epsilon_0}{l^2} \left(\varepsilon^2 + \frac{1}{\lambda_{ab}^2 k_z^2} \ln(1 + \lambda_{ab}^2 k_z^2) \right) \end{aligned} \quad (4)$$

dominating in the dilute limit and at the BZ boundaries $K \simeq K_{BZ}$ or on scales $R \simeq l$. $\varepsilon = \lambda_{ab}/\lambda_c$ is the anisotropy ratio of the HTSC and approximately $\varepsilon \approx 1/5$ in YBCO [1]. The single vortex tilt modulus has a strongly dispersive contribution $c_{44}^{s,em}[k_z]$ from the electromagnetic coupling and an essentially dispersion-free contribution $c_{44}^{s,J}$ from the Josephson coupling (where we neglect a logarithmically dispersive factor in $c_{44}^{s,J}$, which is of the order unity for the relevant wavevectors k_z and magnetic inductions b). The length scale for the onset of dispersion in the bulk contribution c_{44}^b is λ_c because elements of tilted FLs lying in the ab -plane will start to interact on scales $R < \lambda_c$ [29]. As length scale for the onset of dispersion, λ_c occurs as well in the Lindemann criterion (1). The contribution from the electromagnetic coupling to the single vortex tilt modulus gives the local result $c_{44}^s[0] \simeq \epsilon_0/l^2$ for $k_z < 1/\lambda_{ab}$, but its strong dispersion $c_{44}^{s,em}[k_z] \propto k_z^{-2}$ for $k_z > 1/\lambda_{ab}$ leads to its suppression at small wavelengths $k_z > 1/\varepsilon\lambda_{ab}$ where $c_{44}^s \simeq c_{44}^{s,J}$.

From the competition of tilt and shear energy in (2), we can obtain a scaling relation between scales L longitudinal to the FLs and transversal scales R for typical fluctuations involving elastic deformation:

$$L \simeq R \left(\frac{c_{44}[1/R, 1/L]}{c_{66}} \right)^{1/2}. \quad (5)$$

The three-dimensional elastic Hamiltonian (2) is valid only on scales $R > l$ or

$$L > L^* \simeq \left(\frac{c_{44}^s[1/L^*]}{c_{66}} \right)^{1/2}. \quad (6)$$

When we consider fluctuations on scales $L < L^*$ or $R < l$, the FL array breaks up into single FLs described by 1-dimensional elasticity in the longitudinal coordinate z with a line stiffness $\epsilon_l[k_z] = c_{44}^s[k_z]l^2$, because the shear energy containing the effects of FL interactions is always small compared to the tilt energy of the single FL. Thus the interaction-induced length scale L^* separates a regime of “collective” behaviour described by 3D elasticity from a “single vortex” behaviour described by 1D elasticity. L^* starts to increase exponentially in the dilute limit $l/\lambda_{ab} > 1$ due to the exponential decay of c_{66} . For the length scale L^* given by (6), we use therefore the local result $c_{44}^s \approx c_{44}^{s,em} \simeq \epsilon_0/l^2$ determined by the electromagnetic coupling. In the dense limit $l/\lambda_{ab} < 1$, the scale L^* is smaller than $\epsilon\lambda_{ab}$, and $c_{44}^s \approx c_{44}^{s,J} \simeq \epsilon_0\epsilon^2/l^2$, i.e., the dispersion-free contribution from the Josephson coupling dominates. This yields

$$L^* \approx \begin{cases} l < \lambda_{ab} : \epsilon l \\ l > \lambda_{ab} : l \left(\frac{\lambda_{ab}}{l} \right)^{3/4} \exp \left(\frac{l}{2\lambda_{ab}} \right) \end{cases} \quad (7)$$

for the interaction induced length scale L^* in the dense and dilute limits. As we will show below, the criterion (1) is indeed equivalent to a Lindemann criterion in a more conventional form where fluctuations $\overline{u^2}$ on the transversal scale $R \simeq l$ are considered, see (34). Therefore, the topological phase transition can be detected by considering fluctuations of single FLs on the longitudinal scale $L \simeq L^*$.

We focus in this article on the upper branch of the topological transition line in moderately anisotropic compounds as YBCO such that the electromagnetic coupling can essentially be neglected. However, similar to the findings for thermal melting [30], the electromagnetic coupling and its strongly dispersive contribution to the single vortex tilt modulus plays an

important role for the disorder-induced topological phase transition in very anisotropic compounds such as BSCCO [31]. We will consider effects from the electromagnetic coupling in detail in Ref. [32]. We mention here only that in moderately anisotropic HTSC compounds with the upper branch $b_{t,u}(T)$ of the topological phase transition line will lie entirely in the dense regime $b > 2\pi/\kappa^2$, but below the so-called “crossover field” $b_{cr} \sim (2\pi/\kappa^2)(\varepsilon\lambda_{ab}^2/d^2)$ above which $L^* < d$ and the layered structure of the HTSC becomes relevant at the transition line and requires a discrete description in the $\mathbf{c}$ -direction. Only in this regime of magnetic inductions, the strongly dispersive electromagnetic contribution can be neglected at the topological transition (because $L^* < \varepsilon\lambda_{ab}$), while a continuous description in the $\mathbf{c}$ -direction still applies. In the very anisotropic Bi-compounds, however, the upper branch $b_{t,u}(T)$ of the topological phase transition line typically lies in the dilute limit $b < 2\pi/\kappa^2$ where the electromagnetic coupling gives the relevant, strongly dispersive contribution to the single vortex tilt modulus $c_{44}^s \approx c_{44}^{s,em}[k_z] \propto k_z^{-2}$. Because of this dispersion, the behaviour of a single vortex of length L^* changes drastically, and short-scale fluctuations on the (longitudinal) scale $L \simeq \max\{\varepsilon\lambda_{ab}, d\}$ give the main contribution [32]. In the following, we consider the dense regime of a moderately anisotropic compounds such as YBCO and can thus neglect the dispersive electromagnetic contribution and use the dispersion-free, anisotropic result $c_{44}^s \approx c_{44}^{s,J} \simeq \epsilon_0 \varepsilon^2 / l^2$.

At the lower branch of the topological transition line in the dilute limit (where $L^* > \lambda_{ab}$), we have to take into account the electromagnetic coupling and use the isotropic contribution $c_{44}^s \approx c_{44}^{s,em}[0] \simeq \epsilon_0 / l^2$ in the local limit. Furthermore, also in this regime effects from the strong dispersion of $c_{44}^{s,em}[k_z]$ have to be considered. The details of the calculation of the lower branch of the topological transition line will be given in Ref. [32], and we will mention only the main results below.

B. Larkin Length

When point disorder is introduced, every vortex at position $\mathbf{R}_\nu$ in the Abrikosov lattice experiences a pinning potential $V(\mathbf{r})$ with mean zero and short-range correlations

$$\overline{V(\mathbf{r})V(\mathbf{r}')} = \gamma \xi_{ab}^4 \delta_{r_T}^2(\mathbf{R} - \mathbf{R}') \delta_{\xi_c}^1(z - z') , \quad (8)$$

where the overbar denotes an average over the quenched disorder. The strength of the disorder potential is given by $\gamma = n_{pin} f_{pin}^2$, where n_{pin} is the density of pinning centers and f_{pin} the maximum pinning force exerted by one pinning center, and the effective range of the disorder potential is given by

$$r_T = \left(\xi_{ab}^2 + \langle u^2 \rangle_{th}(0, L_\xi) \right)^{1/2} \quad (9)$$

($\langle \dots \rangle_{th}$ denotes a purely thermal average for a fixed $V(\mathbf{r})$), which is equal to the size ξ_{ab} of the core of a vortex at $T = 0$ but broadened by thermal fluctuations at higher temperatures. As proposed in Ref. [1], we introduce the dimensionless disorder strength δ as

$$\delta = \frac{\gamma \xi_{ab}^3}{(\epsilon_0 \xi_{ab})^2} . \quad (10)$$

The interaction with the disorder is described by the Hamiltonian

$$\mathcal{H}_{dis}[\mathbf{u}] = \sum_\nu \int dz V(\mathbf{R}_\nu + \mathbf{u}(\mathbf{R}_\nu, z), z) . \quad (11)$$

For mean square displacements

$$u(R, L) \equiv \overline{\langle (\mathbf{u}(\mathbf{r} + (\mathbf{R}, L)) - \mathbf{u}(\mathbf{r}))^2 \rangle}^{1/2} \quad (12)$$

smaller than the effective scale r_T for variations of the disorder potential V , the FLs explore only *one* minimum of the disorder potential and perturbation theory in the displacements is valid. Expanding in (11) the disorder potential V in $\mathbf{u}$ yields the *random force* theory of Larkin and Ovchinnikov [2]. The (longitudinal) *Larkin length* L_ξ is defined as the crossover scale for the random force regime, at which the average FL displacement becomes of order of the effective range r_T of the point disorder:

$$u(0, L_\xi) \simeq r_T . \quad (13)$$

It is important to note that for HTSCs such as YBCO and BSCCO, the generic disorder strength is such that

$$L_\xi < L^* \quad (14)$$

in the range of magnetic inductions where the elastic Bragg glass will turn out to be stable [33]. Therefore, the random force regime lies entirely in the single vortex regime defined above, and the Larkin length L_ξ is given by the single vortex result L_ξ^s , which is at low temperatures [1]

$$L_\xi^s(0) \simeq \varepsilon \left(\frac{(\varepsilon \epsilon_0 \xi_{ab})^2}{\varepsilon \gamma} \right)^{1/3} \simeq \varepsilon \xi_{ab} \left(\frac{\delta}{\varepsilon} \right)^{-1/3} . \quad (15)$$

This result holds as long as $r_T \simeq \xi_{ab}$. However, above the *depinning temperature* T_{dp}^s of the single vortex, r_T grows beyond ξ_{ab} [1]:

$$r_T^2 \simeq \xi_{ab}^2 \left(1 + \exp \left(\left(T/T_{dp}^s \right)^3 \right) \right) , \quad (16)$$

where the depinning temperature T_{dp}^s is given by [1]

$$T_{dp}^s \simeq \varepsilon \epsilon_0 \xi_{ab} \frac{\varepsilon \xi_{ab}}{L_\xi^s(0)} \simeq \varepsilon \epsilon_0 \xi_{ab} \left(\frac{\delta}{\varepsilon} \right)^{1/3} . \quad (17)$$

Above T_{dp}^s , $L_\xi^s(T)$ increases exponentially with temperature due to the fact that random forces are only marginally relevant for a single FL with two-component displacements [1]:

$$L_\xi^s(T) \simeq L_\xi^s(0) \begin{cases} T \ll T_{dp}^s : & 1 \\ T > T_{dp}^s : & \left(T/T_{dp}^s \right)^{-1} \exp \left(\left(T/T_{dp}^s \right)^3 \right) \end{cases} \quad (18)$$

Let us discuss estimates of the quantities L_ξ and T_{dp}^s at this point, which provide alternative measures of the disorder strength for a HTSC. In Ref. [23], the disorder strength is given by $T_{dp}^s \approx 10K$ in BSCCO (where $\varepsilon \approx 1/100$), which leads to $\delta/\varepsilon \approx 1$ with (17). This estimate is considerably higher than typical values given in Ref. [1] for weak pinning. Therefore, we will use instead estimates in the range $\delta/\varepsilon \approx 10^{-3} \dots 10^{-1}$ for YBCO in accordance with

Ref. [1] which yield $T_{dp}^s \approx 20 \dots 65\text{K}$ and values of the order of $L_\xi^s(0) \approx 30 \dots 6\text{\AA}$ for the (longitudinal) Larkin length in YBCO.

For higher disorder strengths the $T = 0$ Larkin length $L_\xi^s(0)$ can become *smaller* than the layer spacing d . In YBCO, where $d \approx 12\text{\AA}$, this happens for quite strong disorder $\delta/\varepsilon \gtrsim 2 \cdot 10^{-2}$. Then, each pancake-like FL element of length d is pinned individually and we enter a *strong pinning* regime. This requires a description of pinning at the scale d as the smallest physical length scale in the longitudinal direction. In other words, we have to consider the disorder-induced relative displacement $r_d^2 = \overline{u^2}$ of two pancake vortices in adjacent layers. This has been calculated in Ref. [34] at $T = 0$ by means of an Imry-Ma argument (see also [35]) with the result

$$r_d^2(0) \approx \frac{dU_p}{\epsilon_0 \varepsilon^2 \ln(d^2/\varepsilon^2 r_d^2(0))} \ln^{-1/2} \left(\frac{r_d^2(0)}{2\sqrt{\pi}\xi_{ab}^2} \right), \quad (19)$$

where we introduced the mean-square disorder energy $U_p^2 := \gamma d \xi_{ab}^2$ of a line-segment of length $L \simeq d$. The result (19) is valid for $r_d(0) > \xi_{ab}$, i.e., if the relative displacement exceeds the correlation length of the disorder potential, which is the case just for $d > L_\xi^s(0)$. The equation (19) has to be solved self-consistently, but in the following we will use the estimate obtained in the zeroth iteration

$$r_d^2(0) \simeq \frac{dU_p}{\epsilon_0 \varepsilon^2} \simeq \xi_{ab}^2 \frac{U_p}{T_{dp}^s} \simeq \xi_{ab}^2 \left(\frac{d}{L_\xi^s(0)} \right)^{3/2}. \quad (20)$$

The exponent $3/2 = 2\zeta(1,0)$, see below (22), can be interpreted as the exponent characterizing the end-to-end displacement of a rigid rod that can tilt in a random potential. On scales $L_\xi^s(0) < L < d$, each pancake can be treated as such a rigid rod of length L .

Because the pinning is strong, each pancake remains individually pinned in the presence of thermal fluctuations until the thermal energy T is greater than the typical pinning energy U_p of each pancake. Therefore, the result (20) remains to a good approximation valid in the whole temperature range $T \leq U_p$: $r_d(T) \simeq r_d(0)$. This can be checked in a variational calculation along the lines of Ref. [35]. For YBCO with a disorder strength $\delta/\varepsilon \approx 2 \cdot 10^{-1}$ we find $U_p \simeq 70\text{K}$.

Although the thermally increased Larkin length $L_\xi^s(T)$ becomes equal to the layer spacing d already at a temperature

$$T_{L_\xi=d} \simeq T_{dp}^s \left(1 - \frac{L_\xi^s(0)}{d} \right) < U_p, \quad (21)$$

[in YBCO, we find $T_{L_\xi=d} \simeq 45\text{K}$ for $\delta/\varepsilon \approx 2 \cdot 10^{-1}$], the crossover from the strong pinning on the scale d to collective pinning on the scale of the Larkin length $L_\xi^s(T)$ can happen only at $T \simeq U_p$, where the strongly pinned individual pancakes can thermally depin. This result can be obtained from Ref. [35], where it is shown that perturbation theory gives only a *locally* stable solution in a variational treatment of the pinning problem for two pancake vortices in adjacent layers in the temperature range $T_{L_\xi=d} < T < U_p$ whereas the result (20) represents the *globally* stable solution.

C. Positional Correlation Length R_l

On scales exceeding the Larkin length L_ξ^s , the FLs start to explore many minima of the disorder potential V . However, as long as $u(R, L)$ is smaller than the FL spacing l , FLs are *not* competing for the same minima, and the FLs experience effectively *independent* disorder potentials. This leads to the approximation $\mathcal{H}_{dis}[\mathbf{u}] \approx \int d^3\mathbf{r} \tilde{V}(\mathbf{r}, \mathbf{u}(\mathbf{r}))$ (on longitudinal scales exceeding the layer spacing d), where $\tilde{V}$ has also short-range correlations in $\mathbf{u}$. This regime is referred to as the *random manifold* regime [12]. For a d -dimensional (dispersion-free) elastic manifold with a n -component displacement field $\mathbf{u}$, the scaling behaviour of the $\overline{\langle uu \rangle}$ -correlations is known to be

$$u(0, L) \sim L^{\zeta(d,n)} \quad (22)$$

with a roughness exponent $\zeta(d, n)$. We are interested here in the case $d = 1, n = 2$, which is realized on scales $d, L_\xi^s < L < L^*$ in the single vortex regime, where the FLs are described as 1-dimensional elastic manifolds, and the case $d = 3, n = 2$ on scales $L^* < L < L_l$ (or transversal scales $l < R < R_l$) in the collective regime, where the FL array is described as

3-dimensional elastic manifold. L_l and R_l are the *positional correlation lengths*, which are defined as the crossover scales for the random manifold regime, at which the average FL displacement becomes of the order of the FL distance l :

$$u(R_l, 0) = u(0, L_l) = l . \quad (23)$$

On scales $R > R_l$, where $u(R) > l$, FLs start to compete for the *same* minima, and the periodicity of the FL lattice becomes crucial [5,12]. The FL array reaches its asymptotic behaviour of the Bragg glass phase with only logarithmically diverging $\overline{uu}$ -correlations, i.e., quasi long range positional order. The best estimates available for the roughness exponents are [36]

$$\zeta(1, 2) \approx 5/8 \quad \text{and} \quad \zeta \equiv \zeta(3, 2) \approx 1/5 , \quad (24)$$

where the latter occurs also in the above Lindemann criterion (1). In the collective regime the scaling relation (22) gets slightly modified by the dispersion (3) of c_{44}^b to

$$u^2(R, 0) \sim \left(\lambda_c^2 + R^2 \right)^{\zeta(3,2)} , \quad (25)$$

as can be checked by means of a simple Flory-type argument, where we equate the typical disorder energy and elastic energy (2) on *one* dominant scale. (As suggested by a more elaborate variational calculation as in Ref. [12] we neglect possible small logarithmic corrections of order $\ln(1/\varepsilon)$ in (25).) Note that for $l < R < \lambda_c$, the relative displacements (25) are only marginally growing due to the dispersion of c_{44}^b .

The scaling relations (22,25) enable us to obtain the relation between the (transversal) positional correlation length R_l and the (longitudinal) Larkin length L_ξ^s , which will allow us to express R_l in terms of microscopic parameters, both for weak pinning on the scale L_ξ^s (for $L_\xi^s(T) > d$) and for strong pinning of pancakes on the scale d (for $L_\xi^s(T) < d$).

Applying the scaling relation (22) for the $\overline{uu}$ -correlations to the single vortex random manifold regime on longitudinal scales $L_\xi^s < L < L^*$, we obtain for the case $L_\xi^s(0) > d$ of weak pinning

$$u_* \equiv u(l, 0) \simeq u(0, L^*) \simeq r_T \left(\frac{L^*}{L_\xi^s(T)} \right)^{\zeta(1,2)}. \quad (26)$$

In the same manner we can use (25) in the collective random manifold regime on transversal scales $l < R < R_l$:

$$l^2 = u^2(R_l) \simeq u_*^2 \left(\frac{\lambda_c^2 + R_l^2}{\lambda_c^2 + l^2} \right)^{\zeta(3,2)} \simeq u_*^2 \left(\frac{R_l}{\lambda_c} \right)^{2\zeta(3,2)} \quad (27)$$

with $R_l \gg \lambda_c \gg l$. Using (26,27), R_l can be expressed as

$$R_l(T) \simeq \lambda_c \left(\frac{l}{r_T} \right)^{1/\zeta(3,2)} \left(\frac{L_\xi^s(T)}{L^*} \right)^{\zeta(1,2)/\zeta(3,2)}. \quad (28)$$

With the results (16) for r_T , (7) for L^* , and (18) for $L_\xi^s(T)$ together with $\zeta(3,2) \approx 1/5$ and $\zeta(1,2) \approx 5/8$ (24), this yields the desired expression for R_l :

$$R_l(0) \approx \lambda_c \left(\frac{b}{2\pi} \right)^{-15/16} \left(\frac{\delta}{\varepsilon} \right)^{-25/24}$$

$$R_l(T) \approx R_l(0) \begin{cases} T \ll T_{dp}^s : 1 \\ T > T_{dp}^s : \left(T/T_{dp}^s \right)^{-25/8} \exp \left(\frac{5}{8} \left(T/T_{dp}^s \right)^3 \right) \end{cases}. \quad (29)$$

The weakening of the pinning by thermal fluctuations leads to an exponential increase of $R_l(T)$ for temperatures above the depinning temperature T_{dp}^s similar (and related) to the behaviour of the thermally increased Larkin length $L_\xi^s(T)$. For inductions $b/2\pi = 10^{-4} \dots 10^{-2}$ in the dense limit $b/2\pi > 1/\kappa^2$, a disorder strength $\delta/\varepsilon \approx 10^{-2}$, and $\lambda_c(0) \approx 7500\text{\AA}$, we obtain (transversal) positional correlation lengths $R_l(0) \approx (10^4 \dots 10^6) \cdot \lambda_c \approx 7,5 \cdot (10^{-1} \dots 10)\text{cm}$, which are extremely large indicating that over a wide range of length scales the pre-asymptotic random manifold regimes should be observable rather than the asymptotic Bragg glass regime.

For the case $L_\xi^s(0) < d$ of strong pinning of pancakes on the scale d , we apply (22) for the $\overline{\langle uu \rangle}$ -correlations to the single vortex random manifold regime on longitudinal scales $d < L < L^*$ and obtain for low temperatures

$$u_* \equiv u(R = l, 0) \simeq u(0, L = L^*) \simeq r_d(0) \left(\frac{L^*}{d} \right)^{\zeta(1,2)} \quad (30)$$

instead of (26). Using this and (27), R_l can be expressed as

$$R_l(0) \simeq \lambda_c \left(\frac{l}{r_d(0)} \right)^{1/\zeta(3,2)} \left(\frac{d}{L^*} \right)^{\zeta(1,2)/\zeta(3,2)}. \quad (31)$$

With the results (20) for $r_d(0)$, (7) for L^* , and $\zeta(3,2) \approx 1/5$ and $\zeta(1,2) \approx 5/8$ (24), we obtain for the positional correlation length R_l :

$$R_l(0) \approx \lambda_c \left(\frac{b}{2\pi} \right)^{-15/16} \left(\frac{\delta}{\varepsilon} \right)^{-5/6} \left(\frac{\xi_{ab}}{d} \varepsilon \right)^{5/8} \quad (32)$$

This result is valid for temperatures $T \leq U_p$ and gives a temperature independent, smaller value than (29) in this temperature range. At $T \simeq U_p$, pancakes can thermally depin for strong pinning, and we expect a crossover to the weak pinning result (29) with a pronounced increase of $R_l(T)$ with temperature. In YBCO, strong pinning is realized for $\delta/\varepsilon \gtrsim 2 \cdot 10^{-2}$. For $\delta/\varepsilon \approx 2 \cdot 10^{-1}$ and with the layer spacing $d \approx 12\text{\AA}$, we find $R_l(0) \approx 5 \cdot (10^2 \dots 10^4) \cdot \lambda_c \approx 3, 8 \cdot (10^{-2} \dots 1)\text{cm}$ in the induction range $b/2\pi = 10^{-4} \dots 10^{-2}$ in the dense limit.

III. LINDEMANN CRITERION

Let us now show the equivalence of the Lindemann-like criterion (1) obtained in Ref. [21] to the conventional form of the Lindemann criterion generalized to a disordered system. The Lindemann criterion has been proven as a very efficient phenomenological tool to obtain the thermal melting curves of lattices, e.g. the disorder-free FL lattice. There, it is formulated in its conventional form

$$\langle u^2 \rangle_{th} = c_L^2 l^2, \quad (33)$$

with a Lindemann-number $c_L \approx 0.1 \dots 0.2$. For the thermal melting of the FL array, the main contributions to the left hand side of (33) come from fluctuations on the *shortest* scale, which is in the transverse direction the FL spacing l , i.e., $\langle u^2 \rangle_{th} \approx \langle u^2 \rangle_{th}(l, 0)$ (note that we apply again a convention like (12)). Therefore, the straightforward generalization of (33) to the disorder-induced melting by dislocations is

$$\overline{\langle u^2 \rangle}(l, 0) \simeq \overline{\langle u^2 \rangle}(0, L^*) \equiv u_*^2 = c_L^2 l^2 , \quad (34)$$

where we consider again fluctuations on the shortest scale $R \simeq l$. In Ref. [21], one derivation of the criterion (1) was based on a variational calculation for a layered superconductor in a parallel field. There it was found, that unbound dislocations proliferate indeed on the shortest scale at the topological transition described by (1), i.e., in between every layer and thus with a distance l . This suggests that the use of the conventional phenomenological Lindemann criterion in the form (34) might be one possibility to obtain the topological transition line.

This can be further justified by showing that the criterion (1), obtained in Ref. [21] on the basis of a scaling argument and a variational calculation for a uniaxial model, is actually *equivalent* to the phenomenological Lindemann criterion (34): Considering the relation (27) between u_* and l , it becomes clear that (1) is the analog of the Lindemann criterion (34) formulated in terms of the underlying transversal scales rather than the corresponding displacements. Using (27), the criterion (1) for the stability of the Bragg glass can be written as

$$u_*^2 < c^{-1} l^2 . \quad (35)$$

This is just the above phenomenological Lindemann criterion (34), and we can identify

$$c \approx c_L^{-2} . \quad (36)$$

We see that the equivalence of the criterion (1) to the phenomenological Lindemann criterion (34) includes the agreement of the appearing numerical factors: The value for the Lindemann-number $c_L \approx 0.15$, widely used in the literature, produces a good agreement in (36) with the value $c \approx \mathcal{O}(50)$ obtained by the variational calculation. This equivalence to a scenario where disorder-induced fluctuations on the shortest scale “melt” the FL array favours a first order transition scenario for the topological transition, which could not be excluded in the experiments [17]. As we will see, the quantity u_*^2 is equivalent to the mean

square displacement of the “effective” FL studied in the “cage model” of Ertaş and Nelson [23]. They apply the Lindemann criterion directly in its phenomenological form (34) to the “caged” FL. Using (36,24), we can cast the Lindemann-like criterion (1) into the form

$$R_l > c_L^{-1/\zeta} (l^2 + \lambda_c^2)^{1/2} \approx c_L^{-5} \max \{l, \lambda_c\}. \quad (37)$$

IV. PHASE DIAGRAM

Let us now address the issue of phase boundaries of the topologically ordered Bragg glass in the B-T plane as they follow from the Lindemann-like criterion (1) in the above form (37). The results are summarized in Fig. 1. The boundary of the regime given by (37) defines a *topological transition line* $B_t(T)$, where dislocations proliferate and the topological order of the Bragg glass phase is lost. The upper branch $b_{t,u}(T)$ of this line can be obtained by applying the expressions (29) or (32) for the positional correlation length R_l in the dense limit $b > 2\pi/\kappa^2$ to the criterion (37).

For weak pinning or $L_\xi^s(0) > d$ such that we have collective pinning on the scale L_ξ^s , this yields a condition $b < b_{t,u}(T)$ in the b-T plane with

$$\begin{aligned} b_{t,u}(0) &\approx 2\pi \left(\frac{\delta}{\varepsilon}\right)^{-10/9} c_L^{16/3} \approx 2\pi \left(\frac{\varepsilon \epsilon_0 \xi_{ab}}{T_{dp}^s}\right)^{10/3} c_L^{16/3} \\ b_{t,u}(T) &\approx b_{t,u}(0) \begin{cases} T \ll T_{dp}^s : 1 \\ T > T_{dp}^s : \left(T/T_{dp}^s\right)^{-10/3} \exp\left(\frac{2}{3} \left(T/T_{dp}^s\right)^3\right). \end{cases} \end{aligned} \quad (38)$$

Note that the transition line (38) is identical to the one obtained by Ertaş and Nelson [23] by applying the conventional phenomenological Lindemann criterion to a “cage model” for a single FL (this demonstrates the equivalence of the displacement u_* as defined in (34) to the average displacement of the “caged” FL). Estimates of $b_{t,u}(0)$ strongly depend on the chosen value for the Lindemann number $c_L \approx 0.1 \dots 0.2$. A value $c_L \approx 0.15$ and a disorder strength $\delta/\varepsilon \approx 10^{-2}$ lead to $b_{t,u}(0) \approx 4 \cdot 10^{-2}$ or $B_{t,u}(0) \approx 6T$ with $B_{c2}(0) \approx 150T$. For temperatures

$T < T_{dp}^s$ the transition line is essentially temperature-independent because the mechanism for the proliferation of dislocation loops is purely disorder-driven at low temperatures [21]. For $T > T_{dp}^s$ it increases exponentially due to the very effective weakening of the pinning effects by thermal fluctuations in the single vortex regime.

For $L_\xi^s(0) < d$, i.e., strong pinning of pancakes on the scale d (realized for $\delta/\varepsilon \gtrsim 2 \cdot 10^{-2}$ in YBCO), we obtain instead

$$b_{t,u}(0) \approx 2\pi c_L^{16/3} \left(\frac{\delta}{\varepsilon}\right)^{-4/3} \left(\frac{\xi_{ab}}{d}\varepsilon\right)^{2/3} \quad (39)$$

at low temperatures. This result gives a lower induction for the topological transition than (38) and remains valid up to the temperature $T \simeq U_p$, where pancakes can thermally depin. For $T > U_p$ we expect a pronounced increase of $b_{t,u}(T)$ with temperature and a crossover to the weak pinning result (38), cf. Fig. 1. Estimates for $b_{t,u}(0)$ are again very susceptible to changes in the chosen value for the Lindemann number c_L . For $c_L \approx 0.15$ and $\delta/\varepsilon \approx 2 \cdot 10^{-1}$, we find $b_{t,u}(0) \approx 8 \cdot 10^{-4}$ or $B_{t,u}(0) \approx 0,12\text{T}$ for YBCO.

The estimates for $B_{t,u}(0)$ obtained from (38) and (39) are in qualitative agreement with the experimental results for the magnetic field where in YBCO based superlattices a change in the I-V characteristics has been observed [18]. Both (38) and (39) show that the magnetic induction $b_{t,u}$ at the topological transition decreases for stronger anisotropy or effectively larger disorder strength δ/ε , and the stability region of the topologically ordered Bragg glass shrinks.

At some temperature $T_{x,u}$ above T_{dp}^s (and $T_{L_\xi=d}$), the topological transition line $b_{t,u}(T)$ will terminate in the upper branch of the melting curve $b_{m,u}(T)$, which is

$$b_{m,u}(T) \approx 2\pi c_L^4 \left(\frac{\varepsilon \epsilon_0 \xi_{ab}}{T}\right)^2 \quad (40)$$

in this regime of inductions for the moderately anisotropic compound YBCO [30]. The temperature $T_{x,u}$ can be determined from the condition that the thermally increased Larkin length $L_\xi^s(T)$ becomes equal to the scale L^* of the dominant fluctuations at the melting line and the topological transition line. Because $\overline{\langle u^2 \rangle}(0, L_\xi^s(T)) = \langle u^2 \rangle_{th}(0, L_\xi^s(T))$ at the

thermally increased Larkin length, the Lindemann criteria (33) for thermal melting and (37) in the form (34) for the topological phase transition are indeed fulfilled *simultaneously* if $L^* = L_\xi^s(T)$:

$$\overline{\langle u^2 \rangle}(0, L^*) = \langle u^2 \rangle_{th}(0, L^*) = c_L^2 l^2 . \quad (41)$$

This yields

$$T_{x,u} \simeq T_{dp}^s \ln^{1/3} \left(\left(\frac{\delta}{\varepsilon} \right)^{2/3} c_L^{-2} \right) \quad (42)$$

In YBCO, we find $T_{x,u} \approx 80\text{K}$ with the above estimates $c_L \approx 0.15$ and $\delta/\varepsilon \approx 2 \cdot 10^{-1}$. For $T > T_{x,u}$ beyond the melting curve $b_{m,u}(T)$, the FL array melts into a disordered FL liquid, and the Bragg glass order is destroyed by the thermal fluctuations on small scales where disorder-induced fluctuations are irrelevant, whereas above the transition line $b_{t,u}(T)$ the Bragg glass “melts” by disorder-induced fluctuations, when unbound dislocation loops proliferate. For $T < T_{x,u}$, we find $b_{m,u}(T) > b_{t,u}(T)$, and the melting curve $b_{m,u}(T)$ lies *above* the topological transition line in the b-T plane. Therefore, we expect for temperatures $T < T_{x,u}$ that an amorphous, i.e., topologically disordered vortex glass melts into a vortex liquid at the thermal melting line $b_{m,u}(T)$ and consequently, that the melting transition into a vortex liquid at $b_{m,u}(T)$ is of a different nature below and above $T_{x,u}$. In the experiments reported in Ref. [11], such a change in the properties of the melting transition has indeed been observed in YBCO at a temperature around 75K which is in fairly good agreement with our result for $T_{x,u}$.

Let us now give the main results for the lower branch of the topological transition line $b_{t,l}(T)$ at which the strongly dispersive contribution from the electromagnetic coupling to the single vortex tilt modulus is dominating. At low inductions in the dilute limit $b \ll 2\pi/\kappa^2$, the criterion (37) will be violated due to the exponential decrease of the shear modulus c_{66} , or increase of the interaction-induced length scale L^* (7). At low temperatures $T \simeq 0$, the positional correlation length $R_l(0)$ can be determined also from (28) using the *isotropic* single vortex Larkin length (given by (15) with $\varepsilon = 1$) and the appropriate result for L^* .

Because the isotropic Larkin length is always greater than the layer spacing, the layered structure is irrelevant for the collective pinning at low inductions. The criterion (37) then yields for the lower branch of the topological transition line

$$b_{t,l}(0) \approx \frac{2\pi}{\kappa^2} \ln^{-2} \left(c_L^{16/5} \kappa^{6/5} \delta(0)^{-2/3} \right) \quad (43)$$

Due to the strong dispersion of $c_{44}^{s,em}[k_z]$, the thermal depinning at higher temperatures is more complex and involves several crossover temperatures. However, only above the *isotropic* single vortex depinning temperature $T_{dp,i}^s$ (given by (17) with $\varepsilon = 1$) the positional correlation length is increasing exponentially similarly to the thermally increased isotropic Larkin length. This gives only a weak logarithmic temperature dependence for $T < T_{dp,i}^s$ whereas we find the asymptotics

$$b_{t,l}(T) \sim \frac{25\pi}{2\kappa^2} \left(\frac{T}{T_{dp,i}^s} \right)^{-6}. \quad (44)$$

at temperatures $T \gg T_{dp,i}^s$ well above the isotropic single vortex depinning temperature. At a temperature $T_{x,l}$ ($> T_{dp,i}$), $b_{t,l}(T)$ will terminate in the lower branch of the melting curve $b_{m,l}(T)$, which increases logarithmically with temperature [30]

$$b_{m,l}(T) \approx \frac{2\pi}{\kappa^2} \ln^{-2} \left(\frac{c_L^4 \epsilon_0^2 \lambda_{ab}^2}{T^2} \right). \quad (45)$$

Analogously to the findings for the upper branch of the topological transition line, $T_{x,l}$ can be determined from the condition that the thermally increased isotropic Larkin length becomes equal to the scale L^* at the melting line. This yields

$$T_{x,l} \simeq T_{dp,i}^s \ln^{1/3} \left(c_L^2 \kappa \varepsilon^{2/3} \left(\frac{\delta}{\varepsilon} \right)^{-1/3} \right) \quad (46)$$

With $c_L \approx 0.15$ and $\delta/\varepsilon \approx 10^{-2}$, we obtain $b_{t,l}(0) \approx 0.16(2\pi/\kappa^2) \approx 1 \cdot 10^{-4}$, which is by a factor of 40 smaller than $b_{t,u}(0)$ and experimentally hard to verify due to the small inductions $B_{t,u}(0) \approx 150\text{G}$. Furthermore we find $T_{dp,i} \approx 70\text{K}$ and $T_{x,l} \approx 85\text{K}$. From (43) it is clear that the transition line $b_{t,u}(T)$ increases with the disorder strength so that the stability region of the topologically ordered Bragg glass shrinks.

V. CONCLUSION

In conclusion, we have obtained the region in the phase diagram of YBCO in the B-T plane, where the topologically ordered vortex glass should be observable, and the topological transition lines $B_{t,u}(T)$ and $B_{t,l}(T)$, where dislocation loops proliferate. The resulting phase diagram, as given by the formulae (38), (39), (43), and (44) is depicted in Fig. 1. The results are in qualitative agreement with the experimental data of Ref. [18] if the observed changes in the I-V characteristics are attributed to a topological transition of the disordered vortex array.

The phase diagram is based on the Lindemann-like criterion (1) or (37), which has been obtained by a variational calculation for a uniaxial model and a scaling argument presented in Ref. [21]. We have demonstrated the equivalence to the conventional phenomenological formulation of the Lindemann criterion (34) up to the involved numerical factors, i.e., the Lindemann-number c_L . Our results for the upper branch of the topological transition line $B_{t,u}(T)$ agree with Ref. [23], where the conventional phenomenological Lindemann-criterion was applied to the disorder-induced “melting” in the framework of a “cage model”.

VI. ACKNOWLEDGMENTS

The author thanks T. Nattermann, T. Hwa, and A.E. Koshelev for discussions and support by the Deutsche Forschungsgemeinschaft through SFB 341 (B8) and grant KI 662/1–1.

REFERENCES

- [1] G. Blatter, M.V. Feigelman, V.B. Geshkenbein, A.I. Larkin, and V.M. Vinokur, Rev. Mod. Phys. **66**, 1125 (1994).
- [2] A.I. Larkin, Sov. Phys. JETP **31**, 784 (1970); A.I. Larkin and Y.N. Ovchinnikov, J. Low Temp. Phys. **34**, 409 (1979).
- [3] M.P.A. Fisher, Phys. Rev. Lett. **62**, 1415 (1989).
- [4] M.V. Feigelman, V.B. Geshkenbein, A.I. Larkin, and V.M. Vinokur, Phys. Rev. Lett. **63**, 2303 (1989).
- [5] T. Nattermann, Phys. Rev. Lett. **64**, 2454 (1990).
- [6] D.S. Fisher, M.P.A. Fisher, and D.A. Huse, Phys. Rev. B **43**, 130 (1991).
- [7] R.H. Koch, A. Gupta, G. Koren, M.P.A. Fisher, V. Foglietti, and W.J. Gallagher, Phys. Rev. Lett. **63**, 1511 (1989).
- [8] P.L. Gammel, L.F. Schneemeyer, and D.J. Bishop, Phys. Rev. Lett. **66**, 953 (1991).
- [9] H. Safar, P.L. Gammel, D.J. Bishop, D.B. Mitzi, and A. Kapitulnik, Phys. Rev. Lett. **68**, 2672 (1992).
- [10] N.-C. Yeh, W. Jiang, D.S. Reed, U. Kriplani, and F. Holtzberg, Phys. Rev. B **47**, 6146 (1993); D.S. Reed, N.-C. Yeh, W. Jiang, U. Kriplani, and F. Holtzberg, Phys. Rev. B **47**, 6150 (1993); W. Jiang, N.-C. Yeh, D.S. Reed, U. Kriplani, T.A. Tombrello, A.P. Rice, and F. Holtzberg, Phys. Rev. B **47**, 8308 (1993); D.S. Reed, N.-C. Yeh, W. Jiang, U. Kriplani, D.A. Beam, and F. Holtzberg, Phys. Rev. B **49**, 4384 (1994).
- [11] H. Safar, P.L. Gammel, D.A. Huse, D.J. Bishop, W.C. Lee, J. Giapintzakis, and D.M. Ginsberg, Phys. Rev. Lett. **70**, 3800 (1993).
- [12] T. Giamarchi and P. Le Doussal, Phys. Rev. Lett. **72**, 1530 (1994); Phys. Rev. B **52**, 1242 (1995).

- [13] R. Cubitt, E.M. Forgan, G. Yang, S.L. Lee, D.M. Paul, H.A. Mook, M. Yethiraj, P.H. Kes, T.W. Li, A.A. Menovsky, Z. Tarnawski, and K. Mortensen, *Nature* **365**, 407 (1993).
- [14] J. Villain and J.F. Fernandez, *Z. Phys. B* **54**, 139 (1984).
- [15] J.L. Cardy and S. Ostlund, *Phys. Rev. B* **25**, 6899 (1982).
- [16] S.E. Korshunov, *Phys. Rev. B* **48**, 3969 (1993).
- [17] B. Khaykovich, E. Zeldov, D. Majer, T.W. Li, P.H. Kes, and M. Konczykowski, *Phys. Rev. Lett.* **76**, 2555 (1996).
- [18] H. Obara, M. Anderson, L. Fábrega, P. Fivat, J.-M. Triscone, M. Decroux, and Ø. Fischer, *Phys. Rev. Lett.* **34**, 3041 (1995).
- [19] M. Gingras and D. A. Huse, *Phys. Rev. B* **53**, 15193 (1996).
- [20] S. Ryu, A. Kapitulnik, and S. Doniach, *Phys. Rev. Lett.* **77**, 2300 (1996).
- [21] J. Kierfeld, T. Nattermann, and T. Hwa, *Phys. Rev. B* **55**, 626 (1997).
- [22] D.S. Fisher, *Phys. Rev. Lett.* **78**, 1964 (1997).
- [23] D. Ertas and D.R. Nelson, *Physica C* **272**, 79 (1996).
- [24] Y.Y. Goldschmidt, preprints cond-mat/9609258 and cond-mat/9703166.
- [25] T. Giamarchi and P. Le Doussal, *Phys. Rev. B* **55**, 6577 (1997).
- [26] D. Carpentier, P. Le Doussal, and T. Giamarchi, *Europhys. Lett.* **35**, 379 (1996).
- [27] J. Kierfeld and T. Hwa, *Phys. Rev. Lett.* **77**, 4233 (1996).
- [28] L.I. Glazman and A.E. Koshelev, *Phys. Rev. B* **43**, 2835 (1991).
- [29] E.H. Brandt and A. Sudbø, *Physica C* **180**, 426 (1991).
- [30] G. Blatter, V. Geshkenbein, A. Larkin, and H. Nordborg, *Phys. Rev. B* **54**, 72 (1996).

- [31] In Refs. [23,25], the authors focus on the very anisotropic material BSCCO, although they neglect the electromagnetic coupling.
- [32] J. Kierfeld, in preparation.
- [33] From eqs. (7), (15), and (38) one can check a posteriori that (14) is fulfilled for sufficiently strong disorder $\delta/\varepsilon > c_L^3 \sim \mathcal{O}(10^{-3})$. Disorder strengths in HTSC materials (such as the estimates $\delta/\varepsilon \gtrsim \mathcal{O}(10^{-2})$ used throughout this article) usually fulfill this condition [1].
- [34] A.E. Koshelev, L.I. Glazman, and A.I. Larkin, Phys. Rev. B **53**, 2786 (1996).
- [35] A. Engel, Nucl. Phys. B **410**, 617 (1993).
- [36] T. Halpin-Healy and Y.C. Zhang, Phys. Rep. **254**, 215 (1995).

FIGURES




Fig. 1: Schematic phase diagram in the b - T plane ($b \equiv B/B_{c2}(T)$) showing the stability regime of the topologically ordered Bragg glass phase (hatched region). Its phase boundaries are given by the upper and lower branch $b_{t,u}(T)$ and $b_{t,l}(T)$ (solid lines) of a *topological* transition line, where dislocations proliferate. They terminate in the two branches $b_{m,u}(T)$ and $b_{m,l}(T)$ (dashed lines) of the *melting* curve, where the FL array melts by thermal fluctuations into a (disordered) FL liquid.